



# Masterank Wax, Inc.

## MR 8250 SPECIFICATIONS

Property	Test Method	Min	Max	Typical
Melting point, °C	ASTM D87	79.4	88.0	84.8
°F		175.0	190.4	184.8
Oil Content, wt%	ASTM D721	1.5	2.5	2.0
Color	ASTM D1500	0	<1.0	0.5
Penetration, 1/10mm@77°F	ASTM D1321	15	22	17
FDA	21CFR 172.886	PASS		