



# Masterank Wax, Inc.

## MR 6020 SPECIFICATIONS

Property	Test Method	Min	Max	Typical
Melting point, °C	ASTM D87	60	62	61
°F		140.0	143.6	141.8
Oil Content, wt%	ASTM D721	0	0.5	0.3
Color	ASTM D 156	+28	+30	+30
Penetration, 1/10mm@77°F	ASTM D 1321		16	14
FDA	21CFR 172.886	PASS		