



Masterank Wax, Inc.

MR 5810 SPECIFICATIONS

Property	Test Method	Min	Max	Typical
Melting point, °C °F	ASTM D87	58 136.4	60 140	59 138.2
Oil Content, wt%	ASTM D721		0.5	0.3
Color	ASTM D 156	+28	+30	+30
Penetration, 1/10mm@77°F	ASTM D 1321		15	13
FDA	21CFR 172.886	PASS		